

Technical Data Sheet

PRODUCT	COSMOS LAC NITROCELLULOSE VARNISH N374 – N375
DESCRIPTION/USES	Transparent synthetic varnish to treat, coated and uncoated wooden surfaces . This clear lacquer has excellent adhesion , gives gloss N374 and satin N375 finish.
Viscosity	18-25 sec (Flow Cup DIN4, 20°C)
Density	0.6-0.8 g/L (Density Cup 100cm ³ /20°C, ASTM D – 1475)
Solids w/w	15-20%
VOC content	640 g/L
Flash Point	-104 °C (based on propellant)
Drying time	Touch (20°C, Humidity<65%): 5-10min Through dry (20°C, Humidity <65%) : 1h Maximum hardness: 24 hours
Coverage	5m ² /L
Gloss	<20 (60°) N 375 >90 (60) N 374
Can Pressure	4bar (20 °C) , 8 bar (50 °C)
Contents	400ml
Application	Remove all dust and oil from the surface. Protect the area which you don't want to be painted. Shake the can thoroughly and spray at a distance of 30cm from the surface. Try the spray on testing surface. For better results apply 2-3 thin coats, 3-5 min apart. Best application temperature : 20 °C - 25 °C. High moisture levels affect drying time and the final surface
After use	Spray holding the can inverted for 3". Clean the caps with solvent.
Storage	5-35°C. Do not put in vehicles.