

# Verolac 300°C

## Aluminium



Anticorrosive aluminium paint with resistance to high temperatures. Suitable for metallic surfaces like stoves, chimneys, fireplaces as well as for industrial applications where resistance to high temperature up to 300°C is necessary. It reflects sunrays, is resistant to adverse weather conditions and daylight.

- Anticorrosive aluminium paint
- Resistance to high temperature ( ~ 300°C)

### COLOURS

Available in silver shade.

### PACKAGING

Silver	375 mL	750 mL	2,5L
--------	--------	--------	------

### SPREADING RATE

12 - 14 m<sup>2</sup>/ L per coat on properly prepared surfaces.

### VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **499 g/L** VOCs (ready for use product).

### SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and abraded.

### APPLICATION

Stir well before use. Apply one coat by roller, brush or airless spray gun without dilution and without primer. After application, 24 hours should elapse before warming the painted surface. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.

It is touch dry after 2-3 hours and can be recoated after 24 hours. Drying time depends on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Brush Solvent T 300 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.



### TECHNICAL CHARACTERISTICS

Viscosity	50 -90 sec (FORD CUP#4, 20°C)
Density	0,99 ± 0,02 Kg / L (ISO 2811)

### STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

### SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00  
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00  
T. + 30 210 5589 500, F. + 30 210 4835 007, [www.vitex.gr](http://www.vitex.gr)