

Verolac 300°C

High Temperature



High temperature paint based on special silicone resins and special fire resistant pigments that protect against high temperatures and have excellent corrosion resistance. It is applied on interior and exterior surfaces, giving a solid and flexible film resistant to temperatures up to 350°C. It is suitable for painting metallic surfaces, where temperatures are high, such as stoves, stove pipes, chimneys, fireplaces, boilers, grills, barbecues, etc.

- **High temperature paint based on silicone and special fire resistant pigments**
- **For stoves, stove pipes, chimneys, fireplaces etc**

COLOURS

Available in black.

PACKAGING

Black	375 mL	750 mL
-------	--------	--------

SPREADING RATE

14 – 16 m²/L per coat on properly prepared surfaces.

VOC (Volatile Organic Compounds) CONTENT

EU maximum VOC content limit values (Directive 2004/42/CE) for this product (category **A/i** "One-pack performance coatings", Type **SB**): **500 g/L**. This product contains maximum **498 g/L** VOCs (ready for use product).

SURFACE PREPARATION

Surfaces should be cleaned with Brush Solvent T 300, be smooth and dry, free from dust, grease or rust and abraded.

APPLICATION

Stir well before use. Apply one coat by roller, brush or airless spray gun without dilution and without primer. The thickness of the dry paint film is not necessary to exceed 30 microns. A second layer is not required. After application, 24 hours should elapse before warming the painted surface. Do not apply at temperatures below 5°C, above 35°C and/or relative humidity above 80%.



ATTENTION: The product acquires maximum hardness and corrosion resistance, when after drying is heated gradually to 200°C - 300°C for one hour, where fumes may occur depending on the time that has elapsed between the painting and the achieved heating temperature.

It is touch dry after 3-4 hours, depending on weather conditions (humidity and temperature).

Clean rollers, brushes, floor stains, etc. with Spray Gun Solvent T 350 and then with soapy water or detergent. Use Spray Gun Solvent T 350 to clean spray guns.

TECHNICAL CHARACTERISTICS

Viscosity	40 - 70 sec (FORD CUP#4, 20°C)
Density	1,39 ± 0,02 Kg / L (ISO 2811)

STORAGE

Containers must be kept closed in a cool, dry, well ventilated area protected from direct sunlight at temperatures between 5°C - 38°C.

SAFETY ADVICE

Read label before use. For further instructions - precautions see Material Safety Data Sheet.



T.Θ. 139 Ημερος Τόπος, Ασπρόπυργος Τ.Κ. 193 00
P.O. Box 139 Imeros Topos, Aspropyrgos GR 193 00
T. + 30 210 5589 500, F. + 30 210 4835 007, www.vitex.gr