

ISOMAT AK 22

High performance, extra flexible, polymer-modified adhesive for all tile types, even on vibrating substrates

Description

ISOMAT AK 22 is a high performance, extra flexible, cement-based tile adhesive, enhanced with resins, with no vertical slip and extended open time. Provides high initial and final adhesion strength, extra flexibility and resistance to moisture.

Certified according to EN 12004 and classified as a C2 TE S1 adhesive. CE marked.

Fields of application

ISOMAT AK 22 is suitable for fixing absorbent and non-absorbent tiles (e.g. grès porcellanato), natural stone, decorative bricks, large-format tiles, etc. on walls or floors. Well-suited for applications where extra flexibility, high adhesion and moisture resistance are required (e.g. existing ceramic tile layers, heated floors, metal surfaces, swimming pools, etc.). For indoor and outdoor use.

Technical data

Form:	cementitious powder
Colors:	grey, white
Water demand:	7.75 l/25 kg bag
Application temperature:	from +5°C to +35°C
Application thickness:	up to 15 mm
Pot life:	at least 6 h
Open time:	at least 30 min
Minor adjustments open time:	at least 30 min
Slip:	≤ 0.5 mm
Grouting on walls:	after 3-8 h
Grouting on floors:	after 24 h
Temperature resistance:	from -30°C to +90°C
Deformability (EN 12004-2):	> 2.5 mm

Adhesion strength after:

- 28 days: $\geq 1.90 \text{ N/mm}^2$
- heating in +70°C: $\geq 1.90 \text{ N/mm}^2$
- immersion in water: $\geq 1.50 \text{ N/mm}^2$
- 25 freeze-thaw cycles: $\geq 1.50 \text{ N/mm}^2$

All measurements were conducted according to EN 12004-2.

Directions for use

1. Substrate preparation

The surface to be overlaid must be clean, free of dust, grease, paint, loose material, etc. It is recommended to dampen the substrate before application.

2. Application

ISOMAT AK 22 is gradually added to water under continuous stirring, until a uniform paste is formed. A low speed mixer is recommended for mixing.

The mixture should be left for about 5 minutes to settle, before it is slightly stirred again. The tile adhesive should be spread ("combed") on the substrate with a notched trowel, in order to be uniformly applied on the whole surface. The tiles should be fixed by pressure to the desired position.

The applied mixture must be covered with tiles within 30 minutes in order to avoid film formation, i.e. before the adhesive film starts setting.

Consumption

1.5-4.0 kg/m², depending on the trowel notch size and the nature of the substrate.

Packaging

Available in:

- 5 kg plastic bags in grey and white
- 15 kg paper bags in white
- 25 kg paper bags in grey and white

ISOMAT AK 22



Shelf life – Storage

- 15 kg and 25 kg paper bags:
12 months from production date.
- 5 kg plastic bags:
18 months from production date.

This information is valid as long as the product is stored in original, unopened packaging, in places protected from moisture and frost.

Remarks

- Due to cement content, ISOMAT AK 22 reacts with moisture forming alkaline solutions, so is classified as irritant.
- Very porous surfaces, such as aerated concrete, gypsum boards, chipboards, etc. must be previously primed with UNI-PRIMER acrylic primer.
- Please consult the safety instructions written on the packaging before use.

ISOMAT AK-22 GREY



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

08

EN 12004:2007+A1:2012

DoP No.: ISOMAT AK-22 GREY/1005-01
NB: 2032

Improved deformable cementitious adhesive with reduced slip and extended open time, for internal and external tiling.

Reaction to fire	Class E
Release of dangerous substances	See MSDS
Bond strength, as:	
- initial tensile adhesion strength	≥ 1 N/mm ²
Durability, for	
- tensile adhesion strength after heat ageing	≥ 1 N/mm ²
- tensile adhesion strength after water immersion	≥ 1 N/mm ²
- tensile adhesion strength after freeze thaw cycles	≥ 1 N/mm ²

ISOMAT AK 22



ISOMAT AK-22 WHITE

ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag. Athanasios, Greece 08	
EN 12004:2007+A1:2012 DoP No.: ISOMAT AK-22 WHITE/1006-02 NB: 2032 Improved deformable cementitious adhesive with reduced slip and extended open time, for internal and external tiling.	
Reaction to fire	Class E
Release of dangerous substances	See MSDS
Bond strength, as:	
- initial tensile adhesion strength	≥ 1 N/mm ²
Durability, for	
- tensile adhesion strength after heat ageing	≥ 1 N/mm ²
- tensile adhesion strength after water immersion	≥ 1 N/mm ²
- tensile adhesion strength after freeze thaw cycles	≥ 1 N/mm ²

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: support@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. | Edition: 16.6.20

